

# Data Sheet



## BG40

Reflection factor	
P <sub>d</sub>	0.916

Reference thickness	
d [mm]	1

Spectral values guaranteed		
$\tau_i$ (350nm)	$\geq$	0.8
$\tau_i$ (405nm)	$\geq$	0.93
$\tau_i$ (514nm)	$\geq$	0.97
$\tau_i$ (633nm)	$\leq$	0.57
$\tau_i$ (694nm)	$\leq$	0.16
$\tau_i$ (1060nm)	$\leq$	0.02

Refractive Index n	
n <sub>e</sub> (546.1 nm)	= 1.532
n <sub>d</sub> (587.6 nm)	= 1.530
n <sub>i</sub> (1014.0 nm)	= 1.521
Sellmeier coefficients on request	

Density	
$\rho$ [g/cm <sup>3</sup> ]	2.74

Bubble content	
Bubble class	2

Chemical Resistance	
FR class	0
SR class	5.1
AR class	3.0

Transformation temperature	
T <sub>g</sub> [°C]	313

Thermal expansion	
$\alpha_{30/+70^\circ\text{C}}$ [10 <sup>-6</sup> /K]	11.9
$\alpha_{20/300^\circ\text{C}}$ [10 <sup>-6</sup> /K]	
$\alpha_{20/200^\circ\text{C}}$ [10 <sup>-6</sup> /K]	13.7

Temperature coefficient	
T <sub>K</sub> [nm/°C]	


## Notes


Ionically colored glass  
 Bandpass filter / shortpass filter

Long-term changes in the polished surface are possible under some circumstances.

All data without tolerances are to be understood to be reference values.  
 Guaranteed values are only those values listed in the section "Spectral values guaranteed".

Colorimetric evaluation												
Illuminant	A (Planck T = 2856 K)			Illuminant	Planck T = 3200 K			Illuminant	D65 (T <sub>c</sub> = 6504 K)			
	d [mm]	1	2		3	d [mm]	1		2	3	d [mm]	1
x	0.406	0.374	0.348	x	0.383	0.352	0.327	x	0.283	0.262	0.246	
y	0.421	0.430	0.436	y	0.409	0.415	0.419	y	0.327	0.324	0.321	
Y	78	68	61	Y	79	70	63	Y	82	75	69	
$\lambda_d$ [nm]	501	500	500	$\lambda_d$ [nm]	499	498	498	$\lambda_d$ [nm]	491	490	490	
P <sub>e</sub>	0.09	0.17	0.23	P <sub>e</sub>	0.10	0.17	0.23	P <sub>e</sub>	0.11	0.19	0.25	





**Internal transmittance  $\tau_i$  at reference thickness  $d = 1$  mm**  
**The internal transmittance values, tabulated and graphically represented, are reference values only**

$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$
200	$< 10^{-5}$	500	0.982	800	$4.3 \cdot 10^{-3}$	1100	$1.5 \cdot 10^{-2}$	2200	0.795	3700	$1.2 \cdot 10^{-5}$
210	$< 10^{-5}$	510	0.981	810	$3.4 \cdot 10^{-3}$	1110	$1.7 \cdot 10^{-2}$	2250	0.771	3750	$2.5 \cdot 10^{-5}$
220	$< 10^{-5}$	520	0.979	820	$2.8 \cdot 10^{-3}$	1120	$1.9 \cdot 10^{-2}$	2300	0.760	3800	$4.2 \cdot 10^{-5}$
230	$< 10^{-5}$	530	0.974	830	$2.3 \cdot 10^{-3}$	1130	$2.1 \cdot 10^{-2}$	2350	0.747	3850	$5.4 \cdot 10^{-5}$
240	$< 10^{-5}$	540	0.967	840	$2.1 \cdot 10^{-3}$	1140	$2.4 \cdot 10^{-2}$	2400	0.740	3900	$5.3 \cdot 10^{-5}$
250	$< 10^{-5}$	550	0.956	850	$1.9 \cdot 10^{-3}$	1150	$2.7 \cdot 10^{-2}$	2450	0.727	3950	$4.3 \cdot 10^{-5}$
260	$< 10^{-5}$	560	0.939	860	$1.7 \cdot 10^{-3}$	1160	$3.1 \cdot 10^{-2}$	2500	0.703	4000	$2.0 \cdot 10^{-5}$
270	$< 10^{-5}$	570	0.915	870	$1.6 \cdot 10^{-3}$	1170	$3.3 \cdot 10^{-2}$	2550	0.641	4050	$< 10^{-5}$
280	$< 10^{-5}$	580	0.882	880	$1.6 \cdot 10^{-3}$	1180	$3.7 \cdot 10^{-2}$	2600	0.608	4100	$< 10^{-5}$
290	$< 10^{-5}$	590	0.840	890	$1.7 \cdot 10^{-3}$	1190	$4.1 \cdot 10^{-2}$	2650	0.581	4150	$< 10^{-5}$
300	$< 10^{-5}$	600	0.788	900	$1.8 \cdot 10^{-3}$	1200	$4.6 \cdot 10^{-2}$	2700	0.540	4200	$< 10^{-5}$
310	$2.6 \cdot 10^{-2}$	610	0.726	910	$1.8 \cdot 10^{-3}$	1250	$7.4 \cdot 10^{-2}$	2750	0.436	4250	$< 10^{-5}$
320	0.356	620	0.657	920	$2.0 \cdot 10^{-3}$	1300	0.120	2800	0.170	4300	$< 10^{-5}$
330	0.686	630	0.581	930	$2.1 \cdot 10^{-3}$	1350	0.176	2850	$4.2 \cdot 10^{-2}$	4350	$< 10^{-5}$
340	0.832	640	0.503	940	$2.4 \cdot 10^{-3}$	1400	0.240	2900	$1.5 \cdot 10^{-2}$	4400	$< 10^{-5}$
350	0.894	650	0.424	950	$2.6 \cdot 10^{-3}$	1450	0.319	2950	$5.8 \cdot 10^{-3}$	4450	$1.3 \cdot 10^{-5}$
360	0.923	660	0.349	960	$2.9 \cdot 10^{-3}$	1500	0.400	3000	$2.2 \cdot 10^{-3}$	4500	$2.0 \cdot 10^{-5}$
370	0.938	670	0.279	970	$3.2 \cdot 10^{-3}$	1550	0.483	3050	$8.1 \cdot 10^{-4}$	4550	$3.0 \cdot 10^{-5}$
380	0.947	680	0.217	980	$3.6 \cdot 10^{-3}$	1600	0.560	3100	$2.8 \cdot 10^{-4}$	4600	$4.6 \cdot 10^{-5}$
390	0.954	690	0.165	990	$4.1 \cdot 10^{-3}$	1650	0.626	3150	$9.8 \cdot 10^{-5}$	4650	$7.4 \cdot 10^{-5}$
400	0.959	700	0.123	1000	$4.5 \cdot 10^{-3}$	1700	0.680	3200	$3.0 \cdot 10^{-5}$	4700	$1.2 \cdot 10^{-4}$
410	0.964	710	$8.9 \cdot 10^{-2}$	1010	$5.1 \cdot 10^{-3}$	1750	0.718	3250	$1.0 \cdot 10^{-5}$	4750	$1.6 \cdot 10^{-4}$
420	0.967	720	$6.4 \cdot 10^{-2}$	1020	$5.7 \cdot 10^{-3}$	1800	0.750	3300	$< 10^{-5}$	4800	$2.0 \cdot 10^{-4}$
430	0.970	730	$4.6 \cdot 10^{-2}$	1030	$6.4 \cdot 10^{-3}$	1850	0.774	3350	$< 10^{-5}$	4850	$2.3 \cdot 10^{-4}$
440	0.972	740	$3.2 \cdot 10^{-2}$	1040	$7.1 \cdot 10^{-3}$	1900	0.795	3400	$< 10^{-5}$	4900	$2.3 \cdot 10^{-4}$
450	0.975	750	$2.3 \cdot 10^{-2}$	1050	$8.2 \cdot 10^{-3}$	1950	0.805	3450	$< 10^{-5}$	4950	$2.6 \cdot 10^{-4}$
460	0.977	760	$1.6 \cdot 10^{-2}$	1060	$9.4 \cdot 10^{-3}$	2000	0.812	3500	$< 10^{-5}$	5000	$3.1 \cdot 10^{-4}$
470	0.979	770	$1.1 \cdot 10^{-2}$	1070	$1.1 \cdot 10^{-2}$	2050	0.812	3550	$< 10^{-5}$	5050	$3.8 \cdot 10^{-4}$
480	0.981	780	$8.3 \cdot 10^{-3}$	1080	$1.2 \cdot 10^{-2}$	2100	0.810	3600	$< 10^{-5}$	5100	$4.0 \cdot 10^{-4}$
490	0.982	790	$5.7 \cdot 10^{-3}$	1090	$1.4 \cdot 10^{-2}$	2150	0.808	3650	$< 10^{-5}$	5150	$3.8 \cdot 10^{-4}$